



Brand Name: Artica Aura (CHN)

| | | Kitchen Tissue 2 PLY GSM- 20 | | | Kitchen Tissue 1 PLY GSM- 23.5 | | |
|---------------------|--|---------------------------------|------------|--------------------------|-----------------------------------|--|--|
| Properties | | Unit | Range | Unit | Range | | |
| Basis Weight | | g/m ² (1 ply) | 20.0 ± 1.5 | g/m ² (1 ply) | 23.3 ± 1.5 | | |
| Ply | | ply | 2 | ply | 1 | | |
| Thickness | | µm - 2ply | 200 ± 50 | µm - 1ply | 110 ± 20 | | |
| MD Tensile strength | | gf/25mm-2ply | 2000 ± 360 | gf/25mm-1ply | 1125 ± 205 | | |
| CD Tensile Strength | | gf/25mm-2ply | 1100 ± 250 | gf/25mm-1ply | 740 ± 135 | | |
| MD Elongation | | %-2ply | 20 ± 6 | %-1ply | 20 ± 5 | | |
| MD Wet Tensile | | gf/25mm-2ply | ≥ 300 | gf/25mm-1ply | ≥ 180 | | |
| Brightness | | %ISO-60ply | ≤ 90 | %ISO-60ply | ≤ 90 | | |