



Brand Name: Artica Aura (CHN)

				Napkin Tissue 2 PLY GSM- 16		Napkin Tissue 2 PLY GSM- 17	
				Unit	Range	Range	
Properties							
Basis Weight				g/m ² (1 ply)	16.0 ± 1.0	16.7 ± 1.0	
Ply				ply	2	2	
Thickness				µm - 2ply	170 ± 40	170 ± 25	
MD Tensile strength				gf/25mm-2ply	800 ± 195	1100 ± 200	
CD Tensile Strength				gf/25mm-2ply	520 ± 120	660 ± 220	
MD Elongation				%-1 sheet	10 ± 6	10 ± 5	
MD Wet Tensile				gf/25mm-2ply	> 100	220 ± 4	
Brightness				%ISO-60ply	< 90	≤ 90	