



Brand Name: Artica Aura (CHN)

						Napkin Tissue 1 PLY GSM- 18	Napkin Tissue 1 PLY GSM- 19	Napkin Tissue 1 PLY GSM- 21
Properties	Unit	Range	Range	Range				
Basis Weight	g/m ² (1 ply)	18 ± 1.5	19.0± 1.5	21.0 ± 1.5				
Ply	ply	1	1	1				
Thickness	µm - 1ply	90 ± 20	90 ± 20	> 60				
MD Tensile strength	gf/25mm-1ply	510 ± 110	620 ± 145	720 ± 125				
CD Tensile Strength	gf/25mm-1ply	295 ± 80	360 ± 100	450 ± 100				
MD Elongation	%-1 sheet	10 ± 5	15 ± 4	10 ± 5				
Brightness	%ISO-60ply	≤ 90	≤ 90	> 90				
MD Wet Tensile	gf/25mm-1ply	—	≥ 75	> 120				